 SECURA SECURA B.C. Ltd. Prochowa 42 Street, 04-388 Warsaw, tel. +48 22 8134569, 8130722 fax. +48 22 8132949 www.secura.com.pl ; secura@secura.com.pl		TECHNICAL DATA SHEET		
		INSULATING GLOVES ELSEC (EN 60903:2003 + AC2:2005)		
Certificate: WE/S/878/2007	Data of issue: 12.02.2007	Catalogue no: S5920000	Data Sheet number: KK-001	Page: 1/2

APPLICATION

Insulating gloves ELSEC are applicable for electrical purposes exclusively as the basic personal protective tool for live working at voltages up to 1 kV or as additional protective measure for live working at voltages exceeding 1 kV.

CHARACTERISTIC

ELSEC gloves of insulating material have ergonomic shape and are made from high quality natural latex using fully automated production line. Each glove is individually numbered and electrically tested using computer controlled testing arrangement. Report of this test is attached to each individual glove package. The ergonomic shape and elasticity of glove makes comfortable and easy manual work even when anti perspiration inner cotton glove and/or protector leather gloves are worn over. Five classes of ELSEC glove are produced fulfilling different voltage test requirements. There are:

- 00 (2,5 kV),
- 0 (5 kV),
- 1 (10 kV),
- 2 (20 kV)
- 3 (30 kV)

ELSEC gloves are category RC gloves according to EN 60903:2003 + AC2:2005 standard and have special properties increasing their resistance to:


1. R – acid, oil and ozone. Category R combines the characteristics of categories:
 - A – resistant to acid;
 - H – resistant to oil;
 - Z – resistant to ozone;
2. C – resistant to extremely low temperature.

Three sizes of ELSEC gloves are produced: 8, 9, 10, 11, 12.



Technical characteristic of ELSEC glove according to EN 60903:2003 + AC2:2005

Type		ELSEC 2,5	ELSEC 5	ELSEC 10	ELSEC 20	ELSEC 30
Catalogue number		S5911000	S5912000	S5913000	S5914000	S5915000
Class/Category, acc. to PN-EN60903:2006		00/RC	0/RC	1/RC	2/RC	3/RC
Designation of maximum use voltage	AC, V rms	500	1 000	7 500	17 000	26 500
	DC, V	750	1 500	11 250	25 500	39 750
AC tests	Proof voltage kV, rms	2,5	5	10	20	30
	Maximum proof test current, mA, rms, (routine test)	12	12	14	16	18
	Withstand test voltage kV, rms	5	10	20	30	40

 SECURA SECURA B.C. Ltd. Prochowa 42 Street, 04-388 Warsaw, tel. +48 22 8134569, 8130722 fax. +48 22 8132949 www.secura.com.pl ; secura@secura.com.pl		TECHNICAL DATA SHEET		
		INSULATING GLOVES ELSEC (EN 60903:2003 + AC2:2005)		
Certificate: WE/S/878/2007	Data of issue: 12.02.2007	Catalogue no: S5920000	Data Sheet number: KK-001	Page: 2/2

Type		ELSEC 2,5	ELSEC 5	ELSEC 10	ELSEC 20	ELSEC 30
Catalogue number		S5911000	S5912000	S5913000	S5914000	S5915000
DC tests	Proof test voltage Avg kV	4	10	20	30	40
	Withstand test voltage Avg kV,	8	20	40	60	70
Length, mm		360	360	360	360	360
Size		8, 9, 10, 11,12	8, 9, 10, 11,12	8, 9, 10, 11,12	8, 9, 10, 11,12	9,10, 11,12
Cuff		Straigth	Straigth	Straigth	Straigth	Straigth

COMPOSITION

ELSEC insulating gloves are made in whole from natural latex.

REQUIREMENTS

ELSEC gloves have been positively certified in accordance to type test procedure of EN 60903:2003 + AC2:2005, which was required by European Directive 89/686/EU. This has been confirmed by certificate WE/S/878/2007, which entitled the manufacturer to mark the gloves with CE mark.

The manufacturer declares that each individual glove introduced into the market has been positively electrically tested according to EN 60903:2003 + AC2:2005 standard.

INSTRUCTION IN USE AND LIMITATIONS

1. The use voltage of gloves shall not exceed the maximum use voltage appropriate for given class of gloves.
2. No gloves, not even those held in storage, should be used unless they have been tested within a maximum period of six months.
3. Gloves impaired or leaky shall not be used. In case of any doubts of glove's condition it shall not be used, but shall be controlled according to periodical inspection and electrical retesting requirements. Gloves which become wet in use or by washing shall be dried thoroughly, but not in a manner that will cause the temperature of the gloves to exceed 65 °C and shall be powdered with talcum.
4. Periodic re-testing shall be performed according to requirements of EN 60903:2003 + AC2:2005. For class 00 and class 0 gloves, a check for air leaks and a visual inspection may be considered adequate to detect cracks and damages. However, a routine dielectric test shall be performed for gloves of class 1, 2 and 3. Gloves being used intensively are recommended to be tested within 90 days.

STORAGE

Gloves should be stored in their original container or package at the ambient temperature between +5 °C and +35 °C in dark and dry place, not exposed to direct sunlight, artificial light or other sources of ozone. Care should be taken to ensure that gloves are not compressed or folded.

WARRANTY

The manufacturer provides two years warranty for electro insulating gloves ELSEC.